

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
1 August 2002 (01.08.2002)

PCT

(10) International Publication Number  
**WO 02/059199 A1**

(51) International Patent Classification<sup>7</sup>: **C08L 67/02 //**  
(C08L 67/02, 67:02, 67:04) (C08L 67/02, 67:04, 67:04)

MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,  
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,  
VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/EP02/00739

(22) International Filing Date: 25 January 2002 (25.01.2002)

(25) Filing Language: English

(26) Publication Language: English

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(30) Priority Data:

TO2001A000057 25 January 2001 (25.01.2001) IT

**Declarations under Rule 4.17:**

(71) Applicant (*for all designated States except US*): NOVA-MONT S.P.A. [IT/IT]; Via G. Fauser, 8, I-28100 Novara (IT).

— *as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)*

— *of inventorship (Rule 4.17(iv)) for US only*

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): BASTIOLI, Ca-tia [IT/IT]; Via Della Noce, 16, I-28100 Novara (IT). DEL TREDICI, Gianfranco [IT/IT]; Via Sempione, 31, I-21018 Sesto Calende (IT). GUANELLA, Italo [IT/IT]; Via Cavallè, 3/A, I-28068 Romentino (IT). MILIZIA, Tiziana [IT/IT]; Via XIII Martiri, 8, I-28100 Novara (IT). PONTI, Roberto [IT/IT]; Via Momo, 64, I-28047 Oleggio (IT).

(74) Agents: RAMBELLI, Paolo et al.; Jacobacci & Parnters S.p.A., Corso Regio Parco, 27, I-10152 Torino (IT).

**Published:**

— *with international search report*  
— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: TERNARY MIXTURES OF BIODEGRADABLE POLYESTERS AND PRODUCTS MANUFACTURED FROM THEM

(57) Abstract: The invention relates to a mixture of biodegradable polyesters which includes an aromatic-aliphatic polyester (A), an aliphatic polyester (B) and a polylactic acid polymer (C) in which the concentration of A varies, with respect to (A + B) in the range between 40 and 70 % by weight, and the concentration of C with respect to (A + B + C) is of between 6 and 30 % by weight.

WO 02/059199 A1

Ternary mixtures of biodegradable polyesters and products  
manufactured from them

The present invention relates to mixtures of biodegradable polyesters which include at least three polyesters in proportions whereby it is possible to provide biodegradable film with improved characteristics compared to the individual initial polyesters and demonstrating, in particular, properties of considerable strength, both longitudinally of and transverse the direction of the formation of the film, transparency and rigidity.

Film manufactured from such mixtures will prove particularly useful in food packaging, for mulching, for silage and in various other applications.

The Prior Art

Conventional polymers such as low or high-density polyethylene are characterised not only by excellent flexibility and water resistance, but also by a good level of transparency and by excellent resistance to tearing. These polymers are used, for example, for sacks and bags, as packaging material and as film for agricultural mulching. However, their poor biodegradability has caused a problem of visual pollution which has steadily worsened over the past few decades.

Polymers such as L-poly-lactic, D,L-poly-lactic or D-poly-lactic acid and copolymers thereof are thermoplastic materials which are biodegradable, come from a renewable source, are transparent and have excellent resistance to mould and are thus well suited to packaging food products, contributing to

preserving the organoleptic qualities thereof. These materials, however, break down only slowly in the soil and, if composted, decompose only at high temperatures. However their main drawback is that the thin film obtained under normal conditions, by either the blown or cast methods, has a low tear resistance. In addition, these films are very stiff and thus unsuitable for mulching, for making food packaging bags, bin liners or other packaging films which do, however, require considerable strength.

The aliphatic polyesters, on the other hand, which are mainly constituted by monomers from renewable sources, based on diacids and diols, such as polymers of sebacic, brassylic or azelaic acid, for example, have the huge disadvantage of being highly anisotropic, with regard to resistance to both longitudinal and transverse tearing, and also show extremely poor resistance to longitudinal tearing. These characteristics also make film produced from these resins unsuitable for use in mulching, in food packaging or for bin liners and the like.

Polyhydroxy-acids, such as poly- $\epsilon$ -caprolactone, also have a typical tendency to a transverse orientation.

In order to maintain biodegradable characteristics conforming with the CEN 13432 method, biodegradable aliphatic-aromatic polymers, in particular polymers with the aromatic portion constituted by terephthalic acid and the aliphatic portion constituted by diacid diols, and/or hydroxy acids, with a C2-C20 aliphatic chain, either branched or not (possibly chain extended with isocyanates, anhydrides or epoxides) and, in particular, polymers based on terephthalic acid, adipic acid and butandiol, must contain quantities of terephthalic acid

(as moles of the total acid) not exceeding 55% and preferably not exceeding 50%. Examples of this type of material include Ecoflex by BASF or Eastarbio by Eastman, which are strong but with extremely low moduli, of the order of 100MPa or less.

Binary compounds of polylactic acid and aliphatic polyesters have formed the object of numerous patents. In particular, the Patent EP-0 980894 A1 (Mitsui Chemical) describes a significant improvement in tear resistance and in the balance of mechanical properties in film manufactured from mixtures of polylactic acid and polybutylenesuccinate, with the addition of a plasticizer.

However the films described are not transparent and have fairly low strengths, of the order of 120g according to the JIS P8116 method. In addition, the presence of a plasticizer limits use of the film in contact with food products and, since it ages rather quickly, for use as an agricultural mulch.

The US Patent 5,883,199 describes binary compounds of polylactic acid and polyesters, with a polylactic acid content of between 10 and 90% and with the polyester forming either a continuous or co-continuous phase. The tear resistance of the compounds described here is very poor, however.

Object, characteristics and advantages of the invention

Starting from the need to find a biodegradable material which combined the two properties of transparency and tear resistance, it was a surprise to find that if the three different types of polyester described (lactic acid polymers,

aliphatic polyester derived from diacids/diols and aromatic aliphatic polyester) were combined in specific ratios, there was a critical compositional range in which it was possible to achieve resistance to tearing in both directions, comparable to that of conventional plastics materials such as polyethylene, moduli of elasticity with values found between those of low and high-density polyethylene. It was found, even more surprisingly, that it was possible for the transparency of the ternary mixture of polyesters of the invention to be comparable to that of the individual component materials, even when drawn.

#### Description of the invention

The invention relates to a mixture of biodegradable polyesters which includes:

- (A) an aromatic-aliphatic polyester with a melting point of between 50 and 170°C and preferably of between 80° and 120°C;
- (B) an aliphatic polyester with a molecular weight Mw greater than 40,000, and preferably > 60,000 and a melting point of between 40° and 170°C, preferably of between 50° and 145°C, and even more preferably of between 55° and 130°C;
- (C) a polylactic acid polymer containing at least 75% of L-lactic or D-lactic acid or a combination thereof, with a molecular weight Mw greater than 30,000;

in which the concentration of A varies, with respect to (A+B), in the range between 40% and 70% by weight, and the concentration of C with respect to (A+B+C) is of between 5 and 30%, preferably of between 5 and 20% by weight.

More in particular, in the mixture of the invention:

- (A), the aromatic-aliphatic polyester, is biodegradable according to the CEN13432 standard, it has (at T=23° and

Relative Humidity = 55%) a modulus which is less than 150 MPa, lengthens to breaking point by more than 500% for blown film with a thickness of 25-30 $\mu$ m, tested within three days from production;

(B), the aliphatic polyester, preferably a diacid/diol type and/or a polyhydroxyacid type, has (at T=23°C and Relative Humidity = 55%) a modulus of elasticity of between 200 and 1500 MPa and lengthens to breaking point by more than 20%, preferably more than 100%, for blown film with a thickness of 25-30 $\mu$ m, tested within three days of production;

(C), the polylactic acid polymer, has a modulus of more than 1,500MPa.

The mixture of biodegradable polyesters of the invention is obtained in a process which is carried out in a two-screw or one-screw extruder at a temperature of between 100 and 200°C, either by a one-step method or a method involving separate steps of mixing and then film forming or injection molding and so on.

In the event of film forming being separate from the mixing operation, it is carried out by means of conventional machinery for polyethylene extrusion (high or low density), at a heat in the range of 100° to 200°C, preferably of 140 to 197 and more preferably of 185 to 195°C, with a blowing ratio normally in the range of 1.5 - 5 and a drawing ratio of between 3 and 100, preferably 3 and 25 and produces film with a thickness of between 5 and 50 $\mu$ m.

Films of the invention, with a thickness of between 25-30 $\mu$ m, show a tear resistance in both directions, according to the Elmendorf test, of between 10 and 100 N/mm, preferably of between 15 and 90 N/mm and even more preferably of between 20

and 80N/mm, with a ratio of transverse to longitudinal Elmendorf values of between 4.5 and 0.4, and preferably of between 3 and 0.5. Such films have a modulus of between 150 and 1200 MPa, preferably of between 250 and 1000 MPa and prove biodegradable both in soil and when composted. Such films are also characterised by transparency, understood as transmittance at the entrance port measured on the HAZEGUARD SYSTEM XL-211 in the range between 85 and 90% when formed into a film at a head temperature of between 185° and 200°C.

During the mixing step, type (A) polymers are preferred with an MFI (ASTM standard D 1238 - 89) of between 1 and 10 dg/min, type (B) polymers are preferred with an MFI of between 1 and 10dg/min and (C) type polymers are preferred with an MFI of between 2 and 30dg/min.

The type (A) polymer family comprises polyesters obtained from the reaction of mixtures which contain (a<sup>1</sup>) mixtures of from 35 to 95% moles of adipic acid, or derivatives in the form of esters or mixtures thereof, from 5 to 65% moles of terephthalic acid, or ester derivatives and mixtures thereof, and from 0 to 5 % moles of a sulphur-containing compound, the sum of the percentages of the various components to be 100% (a<sup>2</sup>) a compound with two hydroxyl functions selected from a group consisting of C2 -C 6 alkandiols and C5-C10 cycloalkandiols, the molar ratio (a<sup>1</sup>) : (a<sup>2</sup>) being in the interval between 0.4:1 and 1.5:1, it being possible for the polyester to have a molecular weight Mw of between 5,000 and 50,000, a viscosity of between 30 and 350 g/mole (measured in 50:50 w/w dichlorobenzene/phenol at a concentration of 0.5% of the weight of the polyester at 25°C) and a melting point of between 50 and 170°C, and preferably of between 90 and

120°C. It is also possible to produce the polymer using a compound with at least three groups able to form ester bonds.

The polymer (B) is preferably constituted by dicarboxylic aliphatic acids and aliphatic diols, and possibly also by hydroxy acids. Preferably the polymer (B) is also constituted by hydroxyacids. Examples of diacids which can be used are succinic, oxalic, malonic, glutaric, adipic, pimelic, suberic, undecandioic, dodecandioic, sebacic, azelaic or brassylic acids. Particularly preferred are sebacic, azelaic or brassylic acid, or mixtures thereof.

Specific glycols are ethylene glycol, diethylene glycol, triethylene glycol, polyethylene glycol, 1,2- and 1,3-propylene glycol, dipropylene glycol, 1,3-butandiol, 1,4-butandiol, 3-methyl-1,5-pentandiol, 1,6-hexandiol, 1,9-nonandiol, 1,11-undecandiol, 1,13-tridecandiol, neopentyl glycol, polytetramethylene glycol, 1,4-cyclohexane-dimethanol and cyclohexane-diol. These compounds can be used individually and in combination.

Typical hydroxy acids include C<sub>2</sub>-C<sub>22</sub> hydroxy acids such as, for example, glycolic acid, lactic acid, 3-hydroxybutyric, 4-hydroxybutyric, 3-hydroxyvaleric, 4-hydroxyvaleric and 6-hydroxycaproic acid and so on, and also cyclic esters of hydroxycarboxylic acids such as glycolide, dimers of glycolic acid, epsilon-caprolactone and 6-hydroxycaproic acid. These compounds can be used individually or in combination.

All the compounds mentioned above are combined so as to form polyesters with tensile mechanical characteristics of resistance to elongation > 25% and preferably > 100% with a modulus of between 200 and 1500 MPa for blown film at least



25-30 $\mu$ m thick, with a melting point of between 40° and 170°C, preferably of between 50° and 145°C and more preferably of between 55° and 130°C.

Particularly preferred are polyesters containing more than 50%, and preferably more than 70%, moles with respect to the total acid content of azelaic acid, sebacic acid, brassilic acid or mixture thereof. Also preferred are polyhydroxyacids obtained by process of synthesis from bacteria or plants or other biological processes such as copolymers of hydroxybutyrate and C<sub>5</sub>-C<sub>20</sub> hydroxyacids.

The type B polymers also include polyamide polyesters in which the polyester portion is as described above and the polyamide portion can be caprolactam, an aliphatic diamine such as hexamethylenediamine or even an aminoacid. The B type polyesters may also contain a quantity of less than 5% moles of aromatic diacids. Polycarbonates also belong to the type B polymers.

Biodegradable polyesters forming part of the mixture of the invention can be polymerized by polycondensation or, as in the case of glycolide and the lactones, by the open-ring method, as known in the literature. They can be synthesized also by microorganisms or plants. The polyesters can also be branched polymers, with the introduction of polyfunctional monomers such as glycerine, epoxidized soya oil, trimethylolpropane and the like, or of polycarboxylic acids such as butantetracarboxylic acid. In addition, chain extenders such as difunctional, trifunctional or tetrafunctional anhydrides, for example maleic, trimellitic or pyromellitic anhydride, or epoxy, aliphatic or aromatic iso-cyanates group, can be added to A type polyesters.

The material can be regraded with iso-cyanates either in its molten state, at the end of the polymerization reaction or during extrusion, or in its solid state, as described in the Patent Application Novamont WO 99/28367. The three types, A, B and C, of polymer can also have chain extenders or cross-linking agents added to them during the mixing operation.

Higher concentrations of A than those of the range reported above for the mixture of the invention involve modulus characteristics which are too low, while lower concentrations of A bring a deterioration in laceration characteristics.

Higher concentrations of B than those of the range reported above for mixtures of the invention make the film more unbalanced and less strong, while lower concentrations mean that the film is insufficiently rigid.

Concentrations of C polymer below 5% have no significant effect on the balance of tearing properties in the two directions or on adjustment of the modulus.

Material obtained by mixing the three polymers A, B and C needs no plasticizers, which cause migration problems, especially in the case of food packaging. However, quantities of plasticizer of less than 5% of the polymers (B + C) can be added.

Various other additives can be incorporated into the mixture, such as anti-oxidants, UV stabilizers, heat and hydrolytic stabilizers, flame retardants, slow-release agents or organic or inorganic fillers such as natural fibres, anti-static agents, humectant agents, colourings or lubricants, for example.

In particular, in the production of film by the blown or cast methods, silica, calcium carbonate, talc, kaolin, kaolinite, zinc oxide and various wollastonites can be added, as can, generally speaking, inorganic lamellar substances functionalized or not with organic molecules, which are able to delamellate during the mixing stage with the polymeric mixture, or with one of the individual polymers thereof, so as to form nanocompounds with improved anti-blocking and barrier properties. The various inorganic substances can be used in combination or individually. The concentration of inorganic additives is generally of between 0.05 and 70%, preferably of between 0.5 and 50% and, even more preferably, of between 1 and 30%. Particularly preferred are wollastonites and similar organophile substances.

In the case of natural fibres and fillers, such as cellulose, sisal, ground nuts, corn husks, rice husks, soya and the like, preferred concentrations are of between 0.5 to 70 %, preferably of between 1 and 50%. It is also possible to bulk out these materials with mixed inorganic and plant matter.

Aliphatic acid amides can be added to improve the film-forming characteristics of the material, such as oleamide, stearamide, erucamide, behenamide, N-oleylpalmitamide, N-stearylerucamide and other amides, salts of fatty acids such as aluminium, zinc or calcium stearate and the like. The quantity of these additives varies between 0.05 and 7 parts, and preferably between 0.1 and 5 parts of the polymeric mixture.

The mixture thus obtained can be turned into film by blowing or by extrusion with a flat head. The transparent film is strong, can be bonded perfectly and can be produced in

thicknesses of up to 5µm, either blown or cast. The film can be made into sacks and bags for carrying goods, film and bags for food packaging, stretchable, heat-shrinkable film, film for adhesive tape, for disposable nappy tapes and for decorative coloured tape. Some other main applications are for silage, for "breathable" bags for fruit and vegetables, bags for bread and other food products, film for covering packs of meats, cheese and other food items and yoghurt pots. The film can also be bi-orientated.

Film produced with compounds of the invention can also be used as a sealable component in composite materials with at least one layer of polylactic acid or another polyester, of starch which has or has not been destructured and blends thereof with synthetic or natural polymers, or in a compound material, layered with aluminium and other materials, or can be metallized under vacuum with aluminium, silica or other inorganic materials. The layers can be produced either by co-extrusion or by laminating or by extrusion coating, provided that one layer is paper, fabric or non-woven fabric and the other is a biodegradable material or another material which will not melt at the temperatures required to extrude the film.

The film can be used for agricultural mulching, possibly with the addition of UV stabilizers, either in the form of single layer film or co-extruded with a lower-modulus film, as in the case of starch-based materials, in order to improve UV resistance and barrier properties, and to slow down the speed of decomposition in the air and in the soil.

The material thus obtained can also be used to manufacture fibre for textiles and non-woven fabric, or for fishing nets.

In addition, the non-woven fabric can be used for disposable diapers, sanitary protection and the like. The fibres can also be bonded to special types of paper as reinforcement.

The material can also be used successfully to manufacture sheets for either mono-extruded or co-extruded heat forming, with other polymeric layers such as polylactic acid, other polyesters or polyamides, starch-based materials or other materials, and then heat formed into trays for food packaging, agricultural containers and the like.

Other additives can also be added to the material, such as polyethylene or polypropylene waxes, PET and PTB, polystyrene, ethylene or propylene co-polymers with functional carboxyl groups, carboxylate, methacrylate, acrylate, or hydroxy groups, or it can be combined with such polymers in co-extrusion, co-injection or similar operations. The material can be used as a matrix in a blend with destructured starch, according to methods related in Patents EP-0 327505, EP-0 539541, EP-0 400532, EP-0 413798, EP-0 965615, in which it can bond with the starch.

It can be used as a coating film for biodegradable foam materials based on polyester, polyamides made from thermoplastic starch, complex starch or simply a blend of starch with other polymers, or with the material of the present invention.

The material can also be expanded, alone or mixed with starch or with other polymers for the manufacture of containers for fruit and vegetables, meat, cheese and other food products, of fast food containers or even of foam balls which can be moulded into foam elements for industrial packaging. It can

be used as a foam in the place of polyethylene foam. It can be used in the injection molding field for example in order to produce cutlery, food containers, containers for agriculture and industry, pharmaceutical containers and so on.

It can also find application in the field of textiles and non-woven fabric for clothing, hygiene and industrial products, and also for fishing nets or nets for fruit and vegetables.

The mixture of biodegradable polyesters of the invention will now be described by means of some non-limitative examples.

#### Examples

##### Example 1

Polymers constituting the mixture:

- 50% aliphatic-aromatic polyester (A): Ecoflex 0700 BASF;
- 40% aliphatic polyester (B): Polybutylsebacate made of sebacic acid and butandiol with a monobutylstanoic acid catalyst, as in example 1 of WO 00/55236;
- 10% polylactic acid polymer (C): 4040 Cargill with a 6% D-lactic content (MFI=4 dg/min).

The polymers were mixed in an OMC extruder:

Diameter 58mm; L/D = 36; rpm = 160; heat profile 60-120-160x5-155x2

Absorption = 80A. Delivery = 40kg/h

Film forming on Ghioldi machine:

Diameter = 40mm, L/D = 30; rpm = 45; die: diameter = 100mm; air gap = 0.9mm; land = 12; Delivery 13.5 kg/h

Heat profile: 110-130-145x2; filter temperature 190x2; head temperature = 190x2

Film: width = 400mm; thickness 25µm;

The film thus obtained was subjected to the Elmendorf tear-resistance test, carried out on a Lorentzen & Wettre pendulum. The test was carried out both transversely (Ecross) and longitudinally (Elong). The ratio between the two values (Ecross /Elong) shows the level of isotropy of the film in the two directions.

Transmittance values were determined both at the source port (Tsource)

And at the entrance port (Tentr), was carried out with an XL-211 HAZEGUARD SYSTEM measurer.

The modulus of elasticity (E) values, breakage load ( $\sigma$ ) and breakage elongation ( $\epsilon$ ) were determined in accordance with ASTM D 882-91 with an INSTRON 4502 instrument.

The results of the tests are reported in Table 1

#### Examples 2-11

While maintaining the conditions of mixture extrusion and film forming related in example 1, the percentages of the polymers constituting the mixture were varied. The results of the tests on the film thus produced are given in Table 1. In Example 10, polybutylsebacate was replaced with poly- $\epsilon$ -caprolactone. In example 11 polybutylsebacate was replaced with polybutylsuccinate (Bionolle 1903, Showa Denko).

The results thus obtained demonstrated how the ranges of concentration of the polymers in the mixture are crucial to the simultaneous achievement of considerable mechanical and transparency characteristics of the film, which prove so useful in countless practical applications.

### Examples for comparison

While maintaining the conditions of mixture extrusion and of film forming related in Example 1, binary mixtures were tested, which each time contained only two of the polymers constituting the mixture of the invention. The results of the tests on film thus produced are given in Table 2. In Example 3c, polybutylsebacate was replaced with poly- $\epsilon$ -caprolactone.

Comparison of the data displayed in the two tables is clear evidence of the considerable improvement in the mechanical properties of film manufactured with polymeric mixtures of the invention.



TABLE 1

ES	A %	B %	C %	A / A+B	C / A+B+C	E <sub>cross</sub> N/mm	E <sub>long</sub> N/mm	E <sub>cross</sub> / E <sub>long</sub>	T <sub>source</sub> %	T <sub>entr</sub> %	E (Mpa)	$\sigma$ (MPa)	$\epsilon$ (%)
1	60	30	10	66.6	10	47.8	81	0.59	72.7	89	527	36	458
2	50	40	10	55.5	10	44.9	52.4	0.85	65.2	89.4	549	34	446
3	45	45	10	50.0	10	57.5	20.2	2.84	64.1	89.6	511	36	490
4	40	50	10	44.4	10	49.3	33.1	1.49	63.5	89.9	576	35	450
5	50	30	20	62.5	20	32.5	37.4	0.86	61.8	87.0	776	32	354
6	40	40	20	50.0	20	37.8	42.9	0.88	45.5	87.8	757	31	353
7	20	40	40	33.3	40	7.4	9.1	0.81	41.2	88.5	1321	37	319
8	50	45	5	52.6	5	80.2	17.8	4.5	-	-	328	32	609
9	50	48	2	51.0	2	134	12	11.16	-	-	242	31	674
10	50	40	10	55.5	10	13.9	10.7	1.30	75.0	89.0	567	30	576
11	50	40	10	55.5	10	14.2	13.5	1.02	60.1	88.1	502	37	589

TABLE 2

Es.	A %	B %	C %	E <sub>cross</sub> N/mm	E <sub>long</sub> N/mm	E <sub>cross</sub> / long	T <sub>source</sub> %	T <sub>entr</sub> %	E (Mpa)	$\sigma$ (MPa)	$\epsilon$ (%)
1a	0	50	50	7.1	6.4	1.1	68.5	93	2007	35	60
1b	0	60	40	10.7	5.1	2.09	38.5	90.4	1464	36.5	362
1c	0	40	60	7.8	8.6	0.90	73	92	2018	34	69
2a	50	0	50	8.1	7.2	1.1	57.3	85.6	1416	39	394
2b	60	0	40	12.8	7.8	1.64	36.5	82.1	1122	39	361
3a	60	40	0	194	6.98	27.8	65	87	215	42	499
3b	50	50	0	219	6.14	35.7	75	93	245	41	452
3c	50	50	0	246	8	30.8	80	90	-	-	-
3d	30	70	0	84.8	7	12.1	-	-	281	42	426

CLAIMS

1. A mixture of biodegradable polyesters which includes:  
(A) an aromatic-aliphatic polyester with a melting point of between 50° and 170°C;  
(B) an aliphatic polyester with a molecular weight Mw greater than 40,000 and a melting point of between 40° and 170°C;  
(C) a polylactic acid polymer which contains at least 75% of L-lactic or D-lactic acid, or combinations thereof, with a molecular weight Mw greater than 30,000, in which the concentration of A varies with respect to (A+B) in the range of between 40 and 70% by weight, and the concentration of C with respect to (A+B+C) is of between 5 and 30%, preferably of between 5 and 20% by weight.
2. A mixture of biodegradable polyesters according to Claim 1, in which the modulus of the aromatic-aliphatic polyester (A) is less than 150 MPa and its elongation to breaking is greater than 500% for film with a thickness of between 25-30µm produced by the blown method.
3. A mixture of biodegradable polyesters according to each of the preceding Claims, in which the modulus of elasticity of the aliphatic polyester (B) is of between 200 and 1500 MPa and its elongation to breaking is greater than 25%, preferably >100%, for film with a thickness of between 25-30µm, produced by the blown method.
4. A mixture of biodegradable polyesters according to each of the preceding Claims, in which the modulus of the polylactic acid polymer (C) is greater than 1,500 MPa.

5. A mixture of biodegradable polyesters according to Claim 1, in which:

- the aromatic-aliphatic polyester (A) has a modulus of less than 150MPa, elongation to breaking of more than 500% for film with a thickness of 25-30 $\mu$ m, produced by the blown method;

- the aliphatic polyester (B) has a modulus of elasticity of between 200 and 1500 MPa, elongation to breaking of more than 25%, preferably >100%, for film with a thickness of 25-30 $\mu$ m, produced by bubble forming;

- the polylactic acid polymer (C) has a modulus greater than 1,500 MPa..

6. A mixture of biodegradable polyesters according to each of the preceding Claims, in which the aromatic-aliphatic polyester is biodegradable according to standard CEN13432..

7. A mixture of biodegradable polyesters according to each of the preceding Claims, in which the melting point of the aromatic-aliphatic polyester (A) is of between 50° and 170°C, preferably of between 80° and 120°C.

8. A mixture of biodegradable polyesters according to each of the preceding Claims, in which the molecular weight of the aliphatic polyester (B) is  $M_w \geq 40.000$ , preferably  $\geq 60.000$ , and its melting point is of between 40° and 170°C, preferably between 50° and 145° C and more preferably between 55° and 130° C.

9. Mixture of biodegradable polyesters according to any of the preceding claims in which the polyester (B) is of the diacid / diol type preferably polybutylensebacate, polybutylenazellate, polyethylensebacate, polyesamethylenazellate,

polybutylensuccinate, polybutylenbrassilate, polybutylenaze-lateadipate, polyalchilenbrassilate.

10. Mixture of biodegradable polyesters according to each of the claims 1-8 wherein the polyester (B) is a polyhydroxyacid.

11. Mixture of biodegradable polyesters according to claim 10 wherein the polyester (B) is polycaprolacton and/or its copolymers.

12. Mixture of biodegradable polyesters according to claim 12 wherein the polyester (B) is a polyhydroxyalcanoate.

13. Mixture of biodegradable polyesters according to claim 9 wherein the alifatic polyester (B) contains as diacid, azelaic acid, sebacic acid, brassilic acid, or mixtures thereof in a concentration, with respect to the total acid content, higher than 50% moles, preferably higher than 70% moles.

14. Mixtures of biodegradable polyesters according to any of the preceding claims together with destructirised starch, native starch or modified starch wherein the starch, either complexed or not complexed, is present in a dispersed phase.

15. Film produced from mixtures of biodegradable polyesters according to any of the preceding Claims.

16. Film according to Claim 15, characterised by tear resistance in both directions, according to the Elmendorf test, of between 10 and 100N/mm, preferably of between 15 and 90N/mm and even more preferably of between 20 and 80N/mm.

17. A film according to Claim 16, characterised in that the ratio of transverse to longitudinal tear resistance, according to the Elmendorf test, is of between 4.5 and 0.4.

18. Film according to any of the Claims 15-17, characterised in that the modulus value is of between 150 and 1200 MPa, and preferably of between 250 and 1000 MPa.

19. Use of the film according to any of the Claims 15-18, for food packaging, for containing organic residue and for agricultural mulching.

20. Compact sheet manufactured with mixtures according to Claims 1-14 for food containers, containers for seedlings and industrial containers in general.

21. Foam sheet manufactured with mixtures according to Claims 1-14 for food and other containers and for industrial packaging.

22. Fibres manufactured with mixtures according to Claims 1-10 for textiles and non-woven fabrics used in the hygiene, fashion and industrial sectors.

23. A coating material manufactured with mixtures according to Claims 1-14 for application to paper, textiles, non-woven fabrics or other layers of compact or expanded biodegradable material.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/00739

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08L67/02 //(C08L67/02, 67:02, 67:04), (C08L67/02, 67:04, 67:04)

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 950 678 A (EASTMAN CHEM CO) 20 October 1999 (1999-10-20)	
A	EP 0 990 676 A (CORTEC CORP) 5 April 2000 (2000-04-05)	

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents:

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*G\* document member of the same patent family

Date of the actual completion of the international search

3 June 2002

Date of mailing of the international search report

18/06/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Decocker, L

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 02/00739

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0950678	A	20-10-1999	
		US 5292783 A	08-03-1994
		EP 0950678 A1	20-10-1999
		AT 150058 T	15-03-1997
		AT 199383 T	15-03-2001
		AU 696544 B2	10-09-1998
		AU 4557496 A	06-06-1996
		AU 664831 B2	07-12-1995
		AU 9105091 A	25-06-1992
		BR 9107138 A	05-04-1994
		CA 2095536 A1	31-05-1992
		CN 1324891 A	05-12-2001
		CN 1062740 A	15-07-1992
		CN 1183426 A	03-06-1998
		CN 1183423 A ,B	03-06-1998
		CN 1183433 A ,B	03-06-1998
		CN 1183427 A	03-06-1998
		CN 1183428 A	03-06-1998
		CN 1183429 A	03-06-1998
		DE 69125170 D1	17-04-1997
		DE 69132548 D1	05-04-2001
		DE 69132548 T2	28-06-2001
		EP 0559785 A1	15-09-1993
		EP 0736557 A1	09-10-1996
		FI 932450 A	28-05-1993
		FI 20000496 A	03-03-2000
		IE 914155 A1	03-06-1992
		JP 6504558 T	26-05-1994
		JP 2001354802 A	25-12-2001
		KR 220443 B1	15-09-1999
		KR 245905 B1	15-03-2000
		KR 233885 B1	15-03-2000
		KR 245906 B1	15-03-2000
		MX 9102312 A1	31-01-1994
		NO 931920 A	16-07-1993
		NZ 240799 A	26-01-1994
		SG 47853 A1	17-04-1998
		WO 9209654 A2	11-06-1992
		US 6342304 B1	29-01-2002
		US 5446079 A	29-08-1995
		US 5599858 A	04-02-1997
		US 5580911 A	03-12-1996
		US 5559171 A	24-09-1996
		US 5900322 A	04-05-1999
EP 0990676	A	05-04-2000	
		US 6028160 A	22-02-2000
		EP 0990676 A1	05-04-2000
		US 6156929 A	05-12-2000



CORRECTED VERSION

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
1 August 2002 (01.08.2002)

PCT

(10) International Publication Number  
WO 02/059199 A1

(51) International Patent Classification<sup>7</sup>: C08L 67/02 //  
(C08L 67/02, 67:02, 67:04) (C08L 67/02, 67:04, 67:04)

(21) International Application Number: PCT/EP02/00739

(22) International Filing Date: 25 January 2002 (25.01.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
TO2001A000057 25 January 2001 (25.01.2001) IT

(71) Applicant (for all designated States except US): NOVAMONT S.P.A. [IT/TT]; Via G. Fauser, 8, I-28100 Novara (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): BASTIOLI, Catia [IT/TT]; Via Della Noce, 63, I-28100 Novara (IT). DEL TREDICI, Gianfranco [IT/TT]; Via Sempione, 31, I-21018 Sesto Calende (IT). GUANELLA, Italo [IT/TT]; Via Cavallè, 3/A, I-28068 Romentino (IT). MILIZIA, Tiziana [IT/TT]; Via XIII Martiri, 8, I-28100 Novara (IT). PONTI, Roberto [IT/TT]; Via Momo, 64, I-28047 Oleggio (IT).

(74) Agents: RAMBELLI, Paolo et al.; Jacobacci & Partners S.p.A., Corso Regio Parco, 27, I-10152 Torino (IT).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report

(48) Date of publication of this corrected version:  
12 December 2002

(15) Information about Correction:

see PCT Gazette No. 50/2002 of 12 December 2002, Section II

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: TERNARY MIXTURES OF BIODEGRADABLE POLYESTERS AND PRODUCTS MANUFACTURED FROM THEM

(57) Abstract: The invention relates to a mixture of biodegradable polyesters which includes an aromatic-aliphatic polyester (A), an aliphatic polyester (B) and a polylactic acid polymer (C) in which the concentration of A varies, with respect to (A + B) in the range between 40 and 70 % by weight, and the concentration of C with respect to (A + B + C) is of between 6 and 30 % by weight.

WO 02/059199 A1

THIS PAGE BLANK (USPTO)

THIS PAGE IS